

University of Dundee

Adhesive Hydrogels for Maxillofacial Tissue Regeneration Using Minimally Invasive Procedures

Salzlechner, Christoph; Haghighi, Tabasom; Huebscher, Isabella; Walther, Anders Runge; Schell, Sophie; Gardner, Alexander

Published in:
Advanced Healthcare Materials

DOI:
[10.1002/adhm.201901134](https://doi.org/10.1002/adhm.201901134)

Publication date:
2020

Licence:
CC BY

Document Version
Publisher's PDF, also known as Version of record

[Link to publication in Discovery Research Portal](#)

Citation for published version (APA):

Salzlechner, C., Haghighi, T., Huebscher, I., Walther, A. R., Schell, S., Gardner, A., Undt, G., da Silva, R. M. P., Dreiss, C. A., Fan, K., & Gentleman, E. (2020). Adhesive Hydrogels for Maxillofacial Tissue Regeneration Using Minimally Invasive Procedures. *Advanced Healthcare Materials*, 9(4), [1901134].
<https://doi.org/10.1002/adhm.201901134>

General rights

Copyright and moral rights for the publications made accessible in Discovery Research Portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from Discovery Research Portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain.
- You may freely distribute the URL identifying the publication in the public portal.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Adhesive Hydrogels for Maxillofacial Tissue Regeneration Using Minimally Invasive Procedures

Christoph Salzlechner, Tabasom Haghighi, Isabella Huebscher, Anders Runge Walther, Sophie Schell, Alexander Gardner, Gerhard Undt, Ricardo M. P. da Silva, Cécile A. Dreiss, Kathleen Fan, and Eileen Gentleman*

Minimally invasive surgical procedures aiming to repair damaged maxillofacial tissues are hampered by its small, complex structures and difficult surgical access. Indeed, while arthroscopic procedures that deliver regenerative materials and/or cells are common in articulating joints such as the knee, there are currently no treatments that surgically place cells, regenerative factors or materials into maxillofacial tissues to foster bone, cartilage or muscle repair. Here, hyaluronic acid (HA)-based hydrogels are developed, which are suitable for use in minimally invasive procedures, that can adhere to the surrounding tissue, and deliver cells and potentially drugs. By modifying HA with both methacrylate (MA) and 3,4-dihydroxyphenylalanine (Dopa) groups using a completely aqueous synthesis route, it is shown that MA-HA-Dopa hydrogels can be applied under aqueous conditions, gel quickly using a standard surgical light, and adhere to tissue. Moreover, upon oxidation of the Dopa, human marrow stromal cells attach to hydrogels and survive when encapsulated within them. These observations show that when incorporated into HA-based hydrogels, Dopa moieties can foster cell and tissue interactions, ensuring surgical placement and potentially enabling delivery/recruitment of regenerative cells. The findings suggest that MA-HA-Dopa hydrogels may find use in minimally invasive procedures to foster maxillofacial tissue repair.

Degradable materials are used clinically to repair damaged musculoskeletal tissues, particularly cartilage in the knee, using procedures such as matrix-assisted autologous chondrocyte transplantation (MACT).^[1] However, there are currently no similar procedures that surgically place degradable materials with cells or regenerative factors into maxillofacial tissues to foster the repair of muscle, bone, or cartilage. The lack of materials-based regenerative strategies for maxillofacial tissues stems from the strict design criteria that govern materials surgically placed in the head. Ideally, materials should be suitable for minimally invasive procedures, as they minimize the potential for nerve injury and infection.^[2] However, limited surgical access and the complex and small anatomical structures in the head make standard arthroscopic MACT-like procedures unfeasible, particularly because in maxillofacial applications adhesion of the material to the damaged tissue is likely

C. Salzlechner, T. Haghighi, I. Huebscher, A. R. Walther, Dr. S. Schell, Dr. R. M. P. da Silva, Dr. E. Gentleman
Centre for Craniofacial and Regenerative Biology
King's College London
London SE1 9RT, UK
E-mail: eileen.gentleman@kcl.ac.uk

A. R. Walther
Department of Chemical Engineering
Biotechnology and Environmental Technology
University of Southern Denmark
DK-5230 Odense, Denmark
Dr. S. Schell
Department of Conservative Dentistry
Centre of Dentistry
Oral Medicine and Maxillofacial Surgery
University Hospital Tübingen
72076 Tübingen, Germany


A. Gardner
Department of Mucosal and Salivary Biology
Dental Institute
King's College London
London SE1 9RT, UK

Prof. G. Undt
University Clinic of Dentistry
Department of Oral Surgery
Medical University of Vienna
Sensengasse 2a, 1090 Vienna, Austria

Dr. R. M. P. da Silva
i3S-Instituto de Investigação e Inovação em Saúde and INEB – Instituto de Engenharia Biomédica
Universidade do Porto
Rua Alfredo Allen, 208, 4200-135 Porto, Portugal

Dr. C. A. Dreiss
Institute of Pharmaceutical Science
Franklin-Wilkins Building
King's College London
London SE1 9NH, UK

Dr. K. Fan
Department of Oral and Maxillofacial Surgery
King's College Hospital
London SE5 9RS, UK

 The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/adhm.201901134>.

© 2020 The Authors. Published by WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim. This is an open access article under the terms of the Creative Commons Attribution License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

DOI: 10.1002/adhm.201901134

necessary. Therefore, a therapy that could deliver a material to stimulate repair, like MACT, but via a minimally invasive procedure suitable for maxillofacial applications, has the potential to transform the treatment of a range of degenerative and trauma-related maxillofacial disorders.

Regenerative therapies that aim to deliver a material to maxillofacial tissues are subject to numerous design limitations. First, for many applications, the material should bond to the tissue to facilitate integration. For example, unlike in the knee, where cartilaginous defects leave a reservoir in which a reparative solution/material can be placed, the fibrocartilage of the temporomandibular joint (TMJ) (Figure S2, Supporting Information), which might similarly benefit from MACT, is only a few hundred microns thick.^[3] Therefore, adhesivity is likely required to ensure correct placement. The material should also fully degrade, and importantly for maxillofacial applications which abut the brain, must be completely nontoxic. Moreover, the material should ideally be inexpensive, injectable, easily manufactured from materials already approved for clinical use in maxillofacial applications, and suitable for delivery using equipment available in standard surgical theatres. In addition, the material must be amenable to cross-linking under aqueous conditions (submerged in water), as minimally invasive maxillofacial procedures are often carried out with saline perfusion.

Hyaluronic acid (HA) is a hydrophilic polysaccharide composed of repeating disaccharide units of *N*-acetylglucosamine and *D*-glucuronic acid. HA possesses carboxyl and hydroxyl groups on its backbone suitable for chemical modification,^[4,5] allowing it to be cross-linked to form hydrogels. Moreover, HA can be safely degraded by hyaluronidases, which are ubiquitous in vivo. However, HA is nonadhesive, limiting surgical placement, and provides no sites for integrin-mediated interactions with cells, which may preclude invasion by endogenous cells. 3,4-dihydroxyphenylalanine (Dopa) contains catechol functional groups, the active component of the mussel foot protein, and is known to strongly adhere to inorganic and organic materials through both covalent and noncovalent interactions.^[6] Moreover, its simple chemical structure allows it to be tethered to a range of synthetic and natural polymers.^[6]

To create HA-based hydrogels that are potentially suitable for minimally invasive surgical procedures in maxillofacial applications, we carried out a double modification of 100–150 kDa HA to add both MA and Dopa groups using an aqueous synthesis route (Figure 1A,B). ¹H NMR analysis of MA-HA-Dopa confirmed successful modification of the HA backbone (Figures S3 and S4, Supporting Information), and demonstrated that by modifying the molar ratios of methacrylic anhydride and dopamine hydrochloride to HA, we could achieve both low and high degrees of methacrylation and dopamination with a total degree of modification of between 9% and 35% (Figure 1C). Stable hydrogels could then be formed in the presence of a cross-linker upon application of a standard clinical blue light (400–500 nm, 400–600 mW cm⁻²,^[7] widely available in surgical theatres) (Figure 1D). Nonaqueous protocols for adding Dopa to synthetic and natural polymers have been reported;^[8,9] however, our aqueous synthesis avoids the use of potentially toxic solvents such as dichloromethane, which has been linked to facial nerve paralysis.^[10] Indeed, avoiding potential toxins is particularly important in maxillofacial

applications where biomaterial-mediated neurotoxicity has been reported.^[11]

1% and 3% solutions of 100–150 kDa HA have low viscosities (Figure 1E), rendering precise surgical application troublesome. As we aimed to create a material that could be injected, we first modified the viscosity of MA-HA-Dopa by adding 2% unmodified 1 MDa HA. The addition of unmodified HA increased the extensional viscosities of all formulations by approximately one order of magnitude placing them within the range of reported viscosities for clinically relevant materials that are similarly applied by syringe.^[12] We then optimized hydrogel gelation by cross-linking the material's MA groups with di-thiol linear poly(ethylene glycol) (PEG) (significantly less toxic than standard dithiothreitol, Figure S5, Supporting Information), in the presence of nontoxic concentrations of the visible light photo-initiator Eosin Y (Figure S6, Supporting Information). Upon irradiation, Eosin Y subtracts a hydrogen from the thiol group, leaving a thiyl-radical to undergo a thiol-ene reaction with a MA group.^[13]

The clinical application of in situ gelling materials requires the material to set quickly (≈ 4 min). Therefore, we next used small amplitude oscillatory shear rheology as a function of time to monitor gelation (Figure 1F and Figures S7–S10 and Table S1: Supporting Information). We first observed that for all MA-HA and MA-HA-Dopa (low) formulations, the addition of 2% 1 MDa HA did not have an adverse effect on gelation time. However, while MA-HA and MA-HA-Dopa formulations with low degrees of Dopa (with the exception of 1%, without unmodified HA) gelled in less than 4 min (taken as the cross-over between G' and G''), MA-HA-Dopa with high degrees of Dopa gelled more slowly (>4 min) or not at all. We expect our hydrogels to cross-link through thiol-ene radical addition reactions. However, catechols can scavenge free radicals, acting as polymerization inhibitors.^[14] Here, catechol's ability to scavenge free radicals appeared to inhibit thiol-ene type crosslinks by reducing the number of thiyl radicals available to crosslink the hydrogels with increasing Dopa modification. Although Dopa can also react with free thiols upon oxidation to its quinone form, during photoinitiated cross-linking Dopa exists predominantly in its reduced form.^[15] In short, likely by scavenging free radicals, hydrogels containing more Dopa form fewer crosslinks, an effect that has been previously described in catechol-functionalized thiol-ene polymer networks used as adhesives.^[16] We then assessed MA-HA-Dopa's ability to cross-link under aqueous conditions. We found that MA-HA-Dopa could be pipetted and cross-linked while fully immersed in buffer and still form stable hydrogels (Figure 1G and Movie S1: Supporting Information). Taken together, these observations suggest that nontoxic MA-HA-Dopa hydrogels are suitable for injection and can cross-link in an appropriate time frame during minimally invasive procedures in which the joint space is perfused with buffer. Moreover, the material can potentially be placed while a patient is prone and molded many times, if necessary, prior to gelation.

Dopa is recognized for its adhesive properties; however, stickiness requires the Dopa to be oxidized (Figure 2A).^[6,8] Oxidation can be achieved by adding sodium periodate or hydrogen peroxide,^[8] but these can be biologically toxic. Therefore, we next aimed to determine if we could achieve Dopa oxidation




Figure 1. Monomer synthesis and hydrogel formation. A) Synthesis of MA-HA through reaction of HA with methacrylic anhydride; B) Synthesis of MA-HA-Dopa by coupling MA-HA with dopamine; C) Quantification of HA methacrylation and dopamination; D) Reaction schematic demonstrating the formation of hydrogels. Upon blue light exposure, Eosin Y deprotonates di-thiol PEG, allowing it to react with methacrylate moieties on HA leading to a formation of kinetic chains. This process reduces Eosin Y to a colorless state; E) Viscosity of 1% and 3% (w/v) precursor solutions with and without the addition of 2% (w/v) unmodified 1 MDa HA. Plot shows means and standard deviations, $n = 3$; F) Gelation times for different hydrogel compositions. Gelation times were grouped so that light color indicates fast gelation and darker colors show slower gelation; G) Images showing in aqua application of viscous solution and gelation (see also Movie S1 in the Supporting Information), Scale bar = 10 mm.

under physiological conditions that would promote tissue interactions. After 24 h in cell culture medium, MA-HA-Dopa hydrogels turned brown, indicating Dopa oxidation^[8] (Figure 2B). This was confirmed by colorimetric measurements (Figure 2C), and absorption between 250–500 nm continued to increase

over 72 h, confirming that atmospheric oxygen was sufficient to oxidize the Dopa moiety. However, oxidation could be slowed by maintaining hydrogels under hypoxic conditions (5% O_2), showing that lower, tissue-like levels of O_2 , could also foster the process. Next, to determine if the Dopa moiety allowed




Figure 2. Dopa oxidation of hydrogels and tissue interactions. A) Diagram highlighting how Dopa oxidation impacts protein, cell and tissue interactions with hydrogels; B) Images of hydrogels captured directly after gelation (left) or after 24 h incubation in cell culture media (right) showing that the hydrogel becomes brown indicating oxidation of the Dopa; Scale bar = 10 mm; C) Colorimetric measurements of Dopa oxidation in hydrogels maintained in cell culture media under standard or hypoxic (5% O₂) conditions; D) Force required to push hydrogel (3%, high MA, low Dopa; high MA, no Dopa) out of circular defect created in porcine articular cartilage, either after being actively oxidized with NaIO₄ or passively oxidized in cell culture media over 72 h. Plots show means and standard deviations, $n = 3$; unpaired t -test (two-tailed, ** $p < 0.01$, **** $p < 0.0001$); E) Images showing hydrogel (3%, high MA, low Dopa) adherent to muscle tissue (top). As the damaged muscle tissue is pulled apart, the hydrogel remains adherent to the tissue surfaces (bottom) (see also Movies S2 and S3 in the Supporting Information).

for tissue interactions, we formed MA-HA and MA-HA-Dopa hydrogels within a circular defect punched out of porcine articular cartilage. We then either actively oxidized the Dopa (NaIO₄) or allowed it to undergo passive oxidation in cell culture media before measuring the force required to push the hydrogel out of the tissue. We found that both actively and passively oxidized Dopa-modified hydrogels required significantly higher push out forces than their MA-HA counterparts (Figure 2D). To further demonstrate hydrogel-tissue interactions, we then placed MA-HA and MA-HA-Dopa hydrogels along the cut surfaces of a mouse hind limb muscle (Figure 2E and Figures S11 and S12: Supporting Information). While MA-HA hydrogels fell away from the tissue upon manipulation, MA-HA-Dopa hydrogels bonded to the tissue and remained adherent even as the muscle was physically manipulated (Movie S2, Supporting Information), an effect that was maintained after 5 days in culture (Movie S3, Supporting Information).

Materials-based strategies to regenerate cartilage, bone and muscle often call for the presence of cells that can secrete tissue-specific ECM.^[17] Therefore, we next aimed to study cell interactions with MA-HA-Dopa hydrogels. We first seeded 171A4 cells on the surface of hydrogels and examined their attachment. In line with previous observations,^[5,18] cells do not adhere to MA-HA hydrogels (Figure 3A); however, 16 h after seeding, 171A4 cells were adherent to MA-HA-Dopa hydrogels. HA has no sites for integrin-mediated interactions, so cells do not attach to it, even in the presence of serum proteins. Therefore, these observations suggest that Dopa fostered integrin-mediated interactions with the hydrogel, likely by binding proteins^[6,19] through which cells attached. Many tissue engineering strategies also aim to deliver cells within a material. Therefore, we also encapsulated primary human marrow stromal cells (hMSC) within hydrogels and found that the addition of Dopa significantly increased cell viability (Figure 3B and




Figure 3. Hydrogel interactions with cells and physical characterization. A) Bright-field images of 171A4 cells attached to MA-HA and MA-HA-Dopa hydrogels after 18 h of culture. Very few cells were observed attached to MA-HA hydrogels. Scale bar = 200 μ m; B) hMSC survival after 24 h encapsulation within hydrogels. In 3% hydrogels, cells show significantly higher viability in MA-HA-Dopa hydrogels compared to MA-HA hydrogels. $n = 3$ biological replicates, 300 cells per condition, Fisher's exact test, $**p < 0.01$; C) Stiffness as determined by the elastic modulus G' after 4 min light exposure. G' values were grouped such that lighter colors indicate softer and darker colors show stiffer hydrogels; D) Time for full enzymatic degradation of different hydrogel formulations. Lighter colors indicate fast degradation and darker colors show slower degradation. X indicates the absence of gel formation.

Figure S13: Supporting Information). This confirmed previous reports that hMSC can survive within HA-based hydrogels lacking adhesive motifs,^[20] but that the addition of Dopa could enhance cell survival. Taken together, these observations show that by providing sites for protein interaction and thus integrin-mediated interactions, MA-HA-Dopa hydrogels can potentially deliver viable cells or be infiltrated by endogenous cells made available using procedures such as microfracture.^[21]

As hydrogel physical properties will influence both their performance in vivo and subsequent cell response,^[22] we next examined hydrogel stiffness (G') and swelling behavior. 3% hydrogels tended to be stiffer and swell more than those formed with 1% (Figure 3C and Figure S14 and Tables S2–S4: Supporting Information). Moreover, and in line with observations of gelling time, more extensive Dopa modification tended to result in lower values of G' . We then examined hydrogel

degradation in the presence of hyaluronidase and confirmed that all compositions were degradable, but that degradation tended to be slower in compositions with higher levels of MA, lower levels of Dopa and in the presence of unmodified 1 MDa HA (Figure 3D and Figure S15: Supporting Information), in line with the catechol-mediated negative impact on network formation. These observations were in line with previous reports of degradability in HA with similar degrees of modification.^[23] The values of G' we observed here are lower than those of many maxillofacial tissues. It is possible to make HA-based hydrogels stiffer;^[18] however, this requires more extensive chemical modification, which can render the material nondegradable. However, hydrogels are suitable for infiltration within porous load-bearing materials, which have recently been used to resurface the articulating surfaces of the TMJ in an open procedure.^[24] Therefore, combining the MA-HA-Dopa

with a porous scaffold could provide mechanical support while retaining the benefits of the MA-HA-Dopa hydrogel for cell/drug delivery.

Finally, as the shelf life of viscous hydrogel precursors will impact their suitability for clinical applications, we next compared gelation after storage at room temperature (RT) and 4 °C for up to 8 days. While low MA hydrogel compositions stored for 1 or 8 days had stiffnesses that were significantly lower than those of freshly prepared hydrogels, suggesting that the functional cross-linking groups were lost during storage, material prepared with high MA modification, and particularly those with low Dopa, formed stable hydrogels with similar stiffnesses to freshly prepared material (Figures S16–S20, Supporting Information). These observations not only show that MA-HA-Dopa precursor solutions can be stored for at least 1 week prior to use, but also suggest that our chemical strategy does not promote the spontaneous formation of Dopa-Dopa cross-links. Moreover, combined with our observation that high Dopa formulations either gelled more slowly than their low/No Dopa counterparts or not at all further suggests that our chemical strategy does not permit the Dopa moiety to participate in hydrogel cross-linking. Taken together, these data suggest that MA-HA-Dopa formulations with high degrees of methacrylation and low degrees of dopamination gel within a suitable time frame, can be stored prior to use, and have physical and adhesive properties appropriate for use in minimally invasive maxillofacial applications.

Maxillofacial tissues are amenable to regeneration. For example, Undt et al. showed that the cartilaginous surfaces of the TMJ could be regenerated upon surgical placement of appropriate cells and materials.^[24] However, in a case series in 7 patients in which autologous chondrocytes combined with a collagen sponge were used to treat severe degeneration of the articular surfaces of the TMJ, two open surgical procedures were required. Here, we identified HA-based hydrogel compositions with mechanical, biological, adhesive and surgical handling properties suitable for delivery via a single minimally invasive procedure, with or without autologous cells. Adhesive materials for cartilage repair have been previously reported; however, 2-step procedures whereby an adhesive intermediate is “painted” onto the native tissue to foster interactions with the hydrogel^[25] are unlikely to be amenable to minimally invasive procedures and the difficult surgical access characteristic of maxillofacial tissues. Others have reported the use of quinine-modified materials to foster tissue adhesion, but these often require oxidizing the material with harsh reagents.^[8,26] Moreover, in many strategies Dopa itself acts as a cross-linker, restricting potential tissue interactions. Our observations here suggest that MA-HA-Dopa hydrogels can foster tissue adhesion and cell attachment in the absence of harsh chemical treatments and complicated surgical procedures, potentially providing a first-of-its-kind therapy for damaged maxillofacial tissues.

Experimental Section

Details of the materials and experimental methods are available in the Supporting Information.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

T.H. and I.H. contributed equally to this work. C.S. was supported by a Diane Trebble Ph.D. Scholarship. E.G. acknowledges a Research Career Development Fellowship from the Wellcome Trust (WT093687) and a Philip Leverhulme Prize from the Leverhulme Trust. The authors are grateful for support from the Rosetrees Trust and the UK Regenerative Medicine Platform “Acellular/Smart Materials–3D Architecture.” R.M.P.d.S. acknowledges the Wellcome Trust (Institutional Strategic Support Fund), King’s College London and the London Law Trust for a King’s Prize Fellowship. The authors wish to thank Dr. R.A. Atkinson for assistance with NMR experiments and the NMR Facility of the Centre for Biomolecular Spectroscopy at King’s College London, which was established with awards from the Wellcome Trust, British Heart Foundation and King’s College London. Surplus hind limb muscle tissue was obtained from adult wild type C57BL/6 mice after the animals had been sacrificed within other projects. Surplus porcine articular cartilage was obtained from the hind limbs of 56-week old pigs that had been sacrificed within other projects using an overdose of sodium pentobarbital. Tissue was used in experiments fresh, on the day it was harvested.

Conflict of Interest

The authors declare no conflict of interest.

Keywords

adhesivity, biomaterials, hydrogels, minimally invasive surgery, tissue engineering

Received: August 19, 2019

Revised: November 29, 2019

Published online: January 14, 2020

- [1] a) G. Knutsen, J. O. Drogset, L. Engebretsen, T. Grontvedt, V. Isaksen, T. C. Ludvigsen, S. Roberts, E. Solheim, T. Strand, O. Johansen, *J. Bone Jt. Surg.* **2007**, *89*, 2105; b) S. Nehrer, R. Dorotka, S. Domayer, D. Stelzeneder, R. Kotz, *Am. J. Sports Med.* **2009**, *37*, 81.
- [2] F. Liu, H. Giannakopoulos, P. D. Quinn, E. J. Granquist, *Cranio-maxillofac Trauma Reconstr.* **2015**, *8*, 88.
- [3] C. A. Bibb, A. G. Pullinger, F. Baldiaceda, *Arch. Oral Biol.* **1993**, *38*, 343.
- [4] a) K. A. Smeds, A. Pfister-Serres, D. Miki, K. Dastgheib, M. Inoue, D. L. Hatchell, M. W. Grinstaff, *J. Biomed. Mater. Res.* **2001**, *54*, 115; b) J. A. Burdick, C. Chung, X. Jia, M. A. Randolph, R. Langer, *Biomacromolecules* **2005**, *6*, 386; c) X. Z. Shu, Y. Liu, Y. Luo, M. C. Roberts, G. D. Prestwich, *Biomacromolecules* **2002**, *3*, 1304.
- [5] S. A. Ferreira, M. S. Motwani, P. A. Faull, A. J. Seymour, T. T. L. Yu, M. Enayati, D. K. Taheem, C. Salzlechner, T. Haghighi, E. M. Kania, O. P. Oommen, T. Ahmed, S. Loaiza, K. Parzych, F. Dazzi, O. P. Varghese, F. Festy, A. E. Grigoriadis, H. W. Auner, A. P. Snijders, L. Bozec, E. Gentleman, *Nat. Commun.* **2018**, *9*, 4049.
- [6] P. Kord Forooshani, B. P. Lee, *J. Polym. Sci., Part A: Polym. Chem.* **2017**, *55*, 9.
- [7] a) A. Santini, I. T. Gallegos, C. M. Felix, *Primary Dent. J.* **2013**, *2*, 30; b) Dentsply Sirona QHL75 Curing Light, <https://www.dentsplysirona.com/content/dam/dentsply/pim/manufacture/Restorative/>

- Accessories/Curing_Lights/Halogen_Lights/QHL75_Curing_Light/QHL75-2d9j1m0-en-1402 (accessed: August 2019).
- [8] B. P. Lee, J. L. Dalsin, P. B. Messersmith, *Biomacromolecules* **2002**, 3, 1038.
- [9] M. Guvendiren, P. B. Messersmith, K. R. Shull, *Biomacromolecules* **2008**, 9, 122.
- [10] R. M. Jacobovich, D. Landau, Y. Bar Dayan, M. Zilberberg, L. Goldstein, *Am. J. Ind. Med.* **2005**, 48, 389.
- [11] J. L. Renard, D. Felten, D. Bequet, *Lancet* **1994**, 344, 63.
- [12] a) J. Nie, A. Yap, X. Wang, *Oper. Dent.* **2018**, 43, 656; b) K. Al-Ahdal, N. Silikas, D. C. Watts, *Dent. Mater.* **2014**, 30, 517.
- [13] C. E. Hoyle, C. N. Bowman, *Angew. Chem., Int. Ed.* **2010**, 49, 1540.
- [14] a) S. A. Chen, L. C. Tsai, *Makromol. Chem.* **1986**, 187, 653; b) A. Galano, A. Perez-Gonzalez, *Theor. Chem. Acc.* **2012**, 131, 6.
- [15] P. K. Forooshani, B. P. Lee, *J. Polym. Sci., Part A: Polym. Chem.* **2017**, 55, 9.
- [16] B. R. Donovan, J. S. Cobb, E. F. T. Hoff, D. L. Patton, *RSC Adv.* **2014**, 4, 61927.
- [17] a) D. A. Foyt, M. D. A. Norman, T. T. L. Yu, E. Gentleman, *Adv. Healthcare Mater.* **2018**, 7, 1700939; b) S. Loaiza, S. A. Ferreira, T. M. Chinn, A. Kirby, E. Tsolaki, C. Dondi, K. Parzych, A. P. Strange, L. Bozec, S. Bertazzo, M. A. B. Hedegaard, E. Gentleman, H. W. Auner, *Biomaterials* **2018**, 183, 102.
- [18] M. Guvendiren, J. A. Burdick, *Nat. Commun.* **2012**, 3, 792.
- [19] H. Y. Liu, T. Greene, T. Y. Lin, C. S. Dawes, M. Korc, C. C. Lin, *Acta Biomater.* **2017**, 48, 258.
- [20] a) L. Bian, M. Guvendiren, R. L. Mauck, J. A. Burdick, *Proc. Natl. Acad. Sci. USA* **2013**, 110, 10117; b) G. Lisignoli, S. Cristino, A. Piacentini, C. Cavallo, A. I. Caplan, A. Facchini, *J. Cell. Physiol.* **2006**, 207, 364; c) H. Zhu, N. Mitsuhashi, A. Klein, L. W. Barsky, K. Weinberg, M. L. Barr, A. Demetriou, G. D. Wu, *Stem Cells* **2006**, 24, 928; d) S. A. Ferreira, P. A. Faull, A. J. Seymour, T. T. L. Yu, S. Loaiza, H. W. Auner, A. P. Snijders, E. Gentleman, *Biomaterials* **2018**, 176, 13.
- [21] a) F. Frehner, J. P. Benthien, *Cartilage* **2018**, 9, 339; b) O. Gottschalk, S. Altenberger, S. Baumbach, S. Krieglstein, F. Dreyer, A. Mehlhorn, H. Horter, A. Topfer, A. Roser, M. Walther, *J. Foot Ankle Surg.* **2017**, 56, 930; c) M. F. Sommerfeldt, R. A. Magnussen, T. E. Hewett, C. C. Kaeding, D. C. Flanagan, *JBJS Rev.* **2016**, 4, 3.
- [22] N. J. Walters, E. Gentleman, *Acta Biomater.* **2015**, 11, 3.
- [23] a) S. K. Hahn, J. K. Park, T. Tomimatsu, T. Shimoboji, *Int. J. Biol. Macromol.* **2007**, 40, 374; b) Y. D. Park, N. Tirelli, J. A. Hubbell, *Biomaterials* **2003**, 24, 893.
- [24] G. Undt, M. Jahl, S. Pohl, S. Marlovits, D. Moser, H. H. Yoon, J. Frank, S. Lang, C. Czerny, G. Klima, E. Gentleman, R. Ewers, *Oral Surg. Oral Med. Oral Pathol. Oral Radiol.* **2018**, 126, 117.
- [25] B. Sharma, S. Fermanian, M. Gibson, S. Unterman, D. A. Herzka, B. Cascio, J. Coburn, A. Y. Hui, N. Marcus, G. E. Gold, J. H. Elisseeff, *Tissue Eng.* **2013**, 5, 2.
- [26] O. Z. Fisher, B. L. Larson, P. S. Hill, D. Graupner, M. T. Nguyen-Kim, N. S. Kehr, L. De Cola, R. Langer, D. G. Anderson, *Adv. Mater.* **2012**, 24, 3032.